

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 04-142301

(43)Date of publication of application : 15.05.1992

(51)Int.Cl.

C08F 2/00
C08G 85/00
G03G 9/087

(21)Application number : 02-267305

(71)Applicant : KAO CORP

(22)Date of filing : 03.10.1990

(72)Inventor : KAWABE KUNIYASU
MATSUMOTO YOKO**(54) PRODUCTION OF BINDING RESIN AND ELECTROPHOTOGRAPHIC DEVELOPER COMPOSITION**

(57)Abstract:

PURPOSE: To produce a binding resin improved in the quantity of charge, the environmental stability of an image and grindability by blending two polymerizable monomer mixtures before performing two polymerization reactions simultaneously in the same reaction vessel.

CONSTITUTION: An alcohol component [e.g. polyoxypropylene-(2,2)--2,2-bis (4-hydroxyphenyl) propane] is mixed with a carboxylic acid component (e.g. maleic acid) to obtain a condensation--polymerizable monomer mixture (A). An aromatic vinyl compound (e.g. styrene) is mixed with an ethylenic monocarboxylic acid (ester) (e.g. methyl acrylate) to obtain an addition-polymerizable monomer mixture (B). 0.001-15wt.% crosslinking agent (e.g. divinylbenzene) and 0.1-20 pts.wt. polymerization initiator (e.g. benzoyl peroxide) are added to 100 pts.wt. polymerizable monomer mixture obtained by mixing component A with component B, and the resulting mixture is simultaneously subjected to polycondensation and polyaddition to obtain a binding resin comprising 10-90 pts.wt. condensation resin and 90-10 pts.wt. addition resin and having a softening point of 95-170° C and a glass transition temperature of 50-80° C.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

Copyright © 1998,2000 Japanese Patent Office